



25% Soft Carbon Graphite PTFE Datasheet

Typical properties of 25% soft carbon graphite PTFE:

Property	Method	Units	Specification
Specific gravity	ASTM D792	g/cm ³	2.080 - 2.120
Tensile strength	ASTM D4894	MPa	≥ 17
Elongation	ASTM D4894	%	≥ 150
Hardness	ASTM D2240	Shore D	≥ 60
Deformation under load (140 Kg/cm ² for 24 h at 23° C)	ASTM D621	%	5 - 7
Permanent deformation (after 24 h relaxation at 23° C)	ASTM D621	%	2 - 4
Coefficient of linear thermal expansion (T = 25 - 100 °C)		10 ⁻⁵ /°C	7 - 12.5
Coefficient of static friction			0.14 - 0.16
Coefficient of dynamic friction			0.12 - 0.14
Volume resistivity	ASTM D257	Ohm/cm	10 ⁴
Aging and weatherability			Stable over 20 years of exposure
Radiation resistance (gamma rays)	low:		Electrical properties unchanged, mechanical properties decreased
Service temperature		C°	-200 / +260

All properties contained in this datasheet should be considered as typical properties and are not to be used for specification purposes. Furthermore, the information set forth herein shall not, in part or in whole, be construed as constituting a warranty, expressed or implied, nor shall it form or be a part of the basis of any bargain with Vital Polymers. THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, ARE EXCLUDED AND SHALL NOT APPLY. This datasheet provides typical properties to be further investigated by buyers/users having technical expertise. The buyer/user, through its own analysis and testing, is solely responsible for making the final selection of the products and for assuming that all performance, safety, and warning requirements for the application are met. Vital Polymers recommends that buyers/users perform evaluation testing under actual service conditions to determine whether the product is suitable for the intended purpose.

Vital Polymers, LLC • 3651 Wright Way Road • Dayton, OH 45424
Phone: (937) 235-6311 • Fax: (937) 235-9223 • www.vitalpolymers.com