

# TECHNICAL DATA SHEET

## fluteck™ P 7500 CA

### PTFE Carbon Compound

#### Product Description.

fluteck™ P 7500 CA PTFE Carbon Compound is a filled compound based on Virgin PTFE containing 25% Carbon Coke for Ram Extrusion, Compression and Isostatic moulding.

#### Product Properties:

- Improved thermal dimensional stability
- Improved creep resistance
- Improved compression strength
- Good cold flow reduction
- Exceptional temperature resistance
- Excellent chemical stability
- Good thermal and electrical conductivity
- Excellent wear resistance
- Excellent resistance to abrasion
- Improved surface hardness

|            | Property   | Method     | Units  | Specification   |
|------------|--|------------|--|-----------------|
| Physical   | Color  | -          | -  | Black           |
|            | Specific gravity   | ASTM D792  | g/cm <sup>3</sup>                              | 2,050 – 2,120   |
|            | Water absorption   | ASTM D570  | %  | 0,03            |
|            | Flamability  | UL 94      |  | V-0             |
| Mechanical | Tensile strength   | ASTM D4745 | MPa  | ≥ 13            |
|            | Elongation   | ASTM D4745 | %  | ≥ 60            |
|            | Hardness   | ASTM D2240 | Shore D  | ≥62             |
|            | Ball Hardness  | ASTM D785  | MPa  | ≥ 30            |
|            | Deformation under load<br>(140 Kg/cm <sup>2</sup> for 24 hrs. At 23°C) | ASTM D621  | %  | 5 – 7,5         |
|            | Permanent deformation<br>(after 24 hrs. Relaxation at 23°C)            | ASTM D621  | %  | 2 – 4           |
|            | Coefficient of static friction   | ASTM D1894 |  | 0,14 – 0,16     |
|            | Coefficient of dynamic friction  | ASTM D1894 |  | 0,12 – 0,14     |
|            | Wear coefficient   |            | cm <sup>3</sup> min 10 <sup>-8</sup><br>Kg m h | 35              |
| Thermal    | Thermal conductivity   | ASTM C177  | W/m·K  | 0,59            |
|            | Coefficient of linear thermal expansion<br>From 25 to 100 °C           | ASTM D696  | 10 <sup>-5</sup> /°C                           | 7 – 12,5        |
| Electrical | Volume resistivity   | ASTM D257  | Ohm·cm   | 10 <sup>4</sup> |
|            | Surfaceresistivity   | ASTM D257  | Ohm  | 10 <sup>3</sup> |

# TECHNICAL DATA SHEET

## fluteck™ P 7500 CA

### PTFE Carbon Compound

#### Typical properties.

fluteck™ P 7500 CA is a PTFE Carbon Compound preferred for parts and components requiring very good mechanical properties.

fluteck™ P 7500 CA offers an excellent combination of properties Typical of the PTFE fluoropolymer resins:

- Service Temperature: fluteck™ P 7500 CA offers excellent resistance to continuous service temperatures – working conditions from -100° C (-148°F) up to 250° C (482°F) and, for limited periods, even to higher temperatures; product's low temperature resistance allows satisfactory performance down to -200° C (-328°F).
- Chemical resistance: fluteck™ P 7500 CA offers high inertness towards nearly all known chemicals. Only attacked elemental alkali metals, chlorine trifluoride and elemental fluorine at high temperature and pressures might affect properties.
- Solvents resistance: fluteck™ P 7500 CA offers insoluble properties in all solvents up to temperatures as high as 300° C (572° F). Certain highly fluorinated oils only swell and dissolve PTFE at temperatures close to the crystalline melting point.

fluteck™ P 7500 CA Carbon Compound enhances some characteristics of virgin PTFE such as wear and compression strength, deformation under load, cold creep, thermal conductivity and dimensional stability.

#### Typical Application.

fluteck™ P 7500 CA PTFE Carbon Compound offers excellent properties in the chemical processing, in automotive industries, in sealing application, in water application (one of the lowest wear rates in fresh water) and in mechanical applications, in general for bushing, sliding pads, and for slide ways for machine tools. High wear resistance, abrasion resistance and good wear compression properties are suitable for the majority of dry bearing applications against hard counter-surfaces.

fluteck™ P 7500 CA PTFE Carbon Compound is widely used in seal applications where high wear resistance is required under high compression, e.g., piston rings for dry compressor, bearings, grooved mechanical support.

fluteck™ P 7500 CA PTFE Carbon Compound is recommended for dry and poorly lubricated applications, suitable in water and steam service, also when a fast dissipation of electric charge is needed.

#### Statement on suitability for contact with foodstuff.

FDA Approved US Regulation

- Code of Federal regulation 21 CFR Ch.1; section 177.1550 Perfluorocarbon Resins of the Food and Drug Administration/US.

EU Regulation

- EU 1935/2004 - 10/2011 on plastic materials and articles to come in contact with food. It is suitable to be used in contact with aqueous, acidic, alcoholic and oily fatty foodstuffs for which stimulants A, B and D2 are used, according to EU Reg.10/2011

#### Storage and Handling.

fluteck™ P 7500 CA PTFE Carbon Compound can be stored for a long period of life and is exceptionally resistant to aging and weather conditions up to 10 years. Specific aging tests carried out on sample exposed to aging and atmospheric conditions, showed no changes in weight and volume.

In case of semi-finished products, before processing or before the machining, it is advisable to store the material for 24 hours in the production area, preferable in a clean and dry place at a temperature of less than 25°C (77°F), preferably between 21-25°C (70-77°F). This is very important when room temperature is low; in such cases the material should be conditioned up to 72 hours in the production area in the recommended temperature range.

#### Safety instruction.

Follow the normal precautions observed with all fluoropolymers.

Please consult the Material Safety Data Sheet and Product Label for information regarding the safe handling of the material. By following all precautions and safety measures, processing, machining, and using these products poses no known health risks. General handling and processing precautions include: 1) Process only in well-ventilated areas. 2) Do not smoke in working areas. 3) Avoid eye contact. 4) Avoid mouth contact. 5) If skin comes into contact with these products during handling, wash with soap and water afterwards. 6) Avoid contact with hot fluoropolymers.

The user must verify that the finished parts, made out of the semi-finished product, are technically suitable for the requested application. The user must also verify that the finished item may not cause any modification to the organoleptic properties of the foodstuff and that the item's technological fitness it is assigned to may be guaranteed.

For each foreign country market, where the articles are introduced into, it is user's responsibility to verify whether both material than articles comply with the applicable laws and regulations.

#### Delivery format.

fluteck™ P 7500 CA PTFE Carbon Compound is supplied in the following shapes and formats:

Semi-finished products: rods, tubes, sheets, tapes, strips. Shapes and sizes as per fluorseals General Size List and/as per customer request.

Machined parts: Shapes and sizes as per customer request.

**Note:** The information contained in this technical data sheet have been collected and ranked on technical data coming from reliable statistic series gathered in the field over the years. All information are intended only as general guidelines for use at user discretion. fluorseals do not guarantee any specific result and do not assume any liability in connection with the use of the products in the described application. None of the information included in this document is to be taken as a licence to operate under, or recommendations to infringe any existing patents. Before the use, the product has to be sampled and tested in the specific application and in the field of use at working condition in order to be approved by the us

Rev: 01/2019

## fluorseals



Company Quality System  
Uni EN ISO 9001:2015  
cert. CISQ N° 061  
First issue 1994

**fluorseals S.p.A.**  
Via Tribolina, 20/22  
24064 Grumello d.M (Bg)  
Italia

P.IVA - C.F - VAT: IT00593110166  
REA: BG 158562  
Reg.Imp: BG 11004  
Cap. Soc. 1.500.000,00 €

T +39 035 4492811  
F +39 035 831410  
info@fluorseals.it  
**fluorseals.it**